

Formation of d -wave superconducting order in a randomly doped lattice

V. M. Loktev ^{*}; Yu. G. Pogorelov

February 1, 2008

Bogolyubov Institute for Theoretical Physics, NAS of Ukraine, Metrologichna str. 14b, 03143 Kiev, Ukraine; CFP and Departamento de Física da Faculdade de Ciências da Universidade do Porto, Rua do Campo Alegre, 687, 4169-007 Porto, Portugal

Abstract

We consider the interplay between superconducting coupling and dopant impurity scattering of charge carriers in planar square lattice systems and examine the physical conditions (doping level, temperature, local symmetry of coupling and scattering potentials) necessary in this model system to obtain a d -wave superconducting order, like that observed in real doped cuprate HTSC materials. Using the Lifshitz model for the disorder introduced into system by dopants, we analyze also the non-uniform structure of such d -wave parameter, including both its magnitude and phase variation. The results indicate that d -wave superconductivity turns possible in a doped metal until it can be destroyed at too high doping levels.

PACS: 71.55.-i, 74.20.-z, 74.20.Fg, 74.62.Dh, 74.72.-h

1 Introduction

The studies of the effect of impurities and defects on superconducting (SC) properties of metals (including SC alloys) began practically as early as the BCS theory had been built. In particular, the classical papers by Anderson [1] and by Abrikosov and Gor'kov [2] indicated a substantial difference between magnetic and non-magnetic impurities in superconductors. If an addition of non-magnetic impurities has practically no effect on the value of transition critical temperature T_c , the presence of spin at impurity atom (leading to the Kondo effect in a normal metal) results in pair-breaking, that is, it transforms a singlet Cooper pair into an unstable triplet and rapidly suppresses T_c . In all the known cases, the s -type, or isotropic, SC order (apart from the heavy-fermion systems, where it pertains

^{*}Author to whom correspondence should be addressed. E-mail: vloktev@bitp.kiev.ua

to the p -type and T_c is extremely low) and, correspondingly, the isotropic gap near the Fermi level were considered.

The discovery of high- T_c superconductivity (HTSC) in copper oxides faced the physicists to a number of problems which still remain a challenge for the theory. Undoubtedly, this includes the issue of HTSC mechanism, the strong dependencies of many (both SC and normal) properties of copper oxides on charge carriers concentration, specifics of weakly doped systems (first of all, existence of a pseudogap at temperatures above T_c), formation of stripe structures, etc. (see, e.g., the review articles [3],[4],[5],[6]). Such a problem is also presented by the impurity effect on SC properties of HTSC systems. These differ from “old” or “conventional” superconductors not only in higher T_c and d -wave anisotropy of the order parameter but also in the fact that here magnetic and non-magnetic impurities change their roles: the former are weak suppressors for T_c [7], [8], while the latter (in particular, Zn substituting Cu in cuprate layers) lead HTSC to a fast decay [7], [10], [11]. Many aspects of impurity effects in superconductors with anisotropic (including d -wave) pairing were already theoretically studied in Refs. [12],[13],[14],[15],[16],[17], using a range of models and approximations. However, these (and many other) papers did not include one of the most essential features of HTSC systems, the fact that they cannot be non-impure.

In other words, most of theoretic approaches to HTSC are based on the concept, formulated and applied in the pioneering works [1],[2]: one starts from an ideal (2D or quasi-2D) metal with given Fermi energy ε_F , defined by the density of free carriers, and then consider perturbation of independently existing SC condensate by some extrinsic (magnetic or non-magnetic) impurities. Their action, local or global, affects the pre-formed and condensed singlet pairs. Of course, this formulation is reasonable but it lacks an essential moment for the conductance in copper oxides: all the HTSC’s are doped metals, where (like the doped semiconductors) each carrier is provided by insertion of a donor or acceptor into the system. In its turn, this implies that HTSC’s are intrinsically impure systems with an inherent disorder,¹ and the number of impurity (“foreign” included) atoms can not be less than at least the number of charge carriers. If one has in normal metals the condition $k_F\ell \gg 1$ (k_F being the Fermi momentum, and ℓ the carrier mean free path between collisions with impurity atoms) [18], it turns to $k_F\ell \sim 1$ in HTSC’s, and they pertain to the family of “*bad*” metals with both k_F and ℓ defined by the doping.

Perhaps, the first attempt to consider in a self-consistent way the characteristic tendencies for HTSC, pairing of the carriers and their localization on impurity atoms, was made in the authors’ work [19]. It discussed the phase diagram of doped 2D metal in presence of s -wave pairing and showed that SC is not possible neither at low impurity concentration $c < c_0 \sim \varepsilon_0/W$ (when all the carriers are localized near impurities with localization energies ε_0 much less of the bandwidth W , so that c_0 is typically few percents) nor at too high

¹Here we don’t consider possible formation of stripe structures, where ordered or disordered distribution of dopants can not be yet confirmed by any reliable data.

c (when the pair inverse lifetime times $\hbar$ exceeds the SC gap). There, in general, the self-consistency is related either to the SC order parameter (like the common Bardeen-Cooper-Schrieffer or Bogolyubov-de Gennes treatments) and to the chemical potential.

The present work is aimed to extend the approach by Ref. [19] to the case of d -wave SC coupling and to trace the formation of the corresponding order parameter. It is motivated, not to the least degree, by an apparent controversy between the experimental evidence for d -symmetry of the order parameter in HTSC [20], [21], [22], and theoretical claim that anisotropic pairing should not survive in presence of chaotically distributed isotropic scatterers [23]. For the sake of simplicity, we restrict the consideration to the doping range $c > c_0$, where the self-consistency is only relevant for the SC order parameter, while the chemical potential can be put² $\mu \approx \varepsilon_F \approx 3cW/4$. Then, we distinguish between two types of impurity effects by doping. The first, the so called homogeneous effects, are displayed by translationally invariant single-particle Green functions (SPGF). They were studied earlier by various means [24] but, as a rule, introducing the disorder through a single parameter V_A of Anderson's model [24]. In contrary, we employ the Lifshitz' model of disorder [25], characterized by two independent parameters: c and the impurity potential V_L . They produce an equivalent $V_A \sim \sqrt{c(1-c)}V_L$, but not vice versa. Within this model, more adequate for doped HTSC systems, we conclude about persistence of d -wave order parameter under homogeneous impurity effects. Also we explicitly consider other type of effects, inhomogeneous, due to local variations of order parameter near impurity centers. This involves *two-particle* Green functions (TPGF), besides usual SPGF, and yields in possible limitation for SC at high enough dopant concentrations.

At least, we would like to appreciate this great honor and also a pleasant opportunity for us to publish this work in the Low Temperature Physics issue dedicated to the memory of outstanding physicist L.V. Shubnikov, whose contribution to the low temperature physics in general and to superconductivity in particular can not be overestimated.

2 Hamiltonian and Green functions

We start from the model electronic Hamiltonian in band representation

$$H = \sum_{\mathbf{k}} \left\{ \sum_{\sigma} \varepsilon_{\mathbf{k}} c_{\mathbf{k},\sigma}^{\dagger} c_{\mathbf{k},\sigma} - \frac{1}{N} \sum_{\mathbf{k}'} \left[V \gamma_{\mathbf{k}} \gamma_{\mathbf{k}'} c_{\mathbf{k},\uparrow}^{\dagger} c_{-\mathbf{k},\downarrow}^{\dagger} c_{-\mathbf{k}',\downarrow} c_{\mathbf{k}',\uparrow} - \right. \right. \quad (1)$$

$$\left. \left. - V_L \sum_{\mathbf{p},\sigma} e^{i(\mathbf{k}'-\mathbf{k})\cdot\mathbf{p}} c_{\mathbf{k}',\sigma}^{\dagger} c_{\mathbf{k},\sigma} \right] \right\},$$

²However, it is known that μ can differ essentially from the Fermi energy ε_F in the limit of very low doping (see, e.g., [4], [6]).

where $c_{\mathbf{k},\sigma}$ and $c_{\mathbf{k},\sigma}^\dagger$ are the Fermi operators for a charge carrier with wavevector $\mathbf{k}$ and spin σ . The simplest band energy $\varepsilon_{\mathbf{k}} = 4t - 2t(\cos ak_x + \cos ak_y)$, with full bandwidth $W = 8t$, is expressed through the amplitude t of carrier hopping between nearest neighbor sites³ (of the total N in the lattice with a constant a). The parameter V models the attraction between two carriers with opposite spins on such sites, the factor $\gamma_{\mathbf{k}} = (\cos ak_x - \cos ak_y)\theta(\varepsilon_D^2 - \xi_{\mathbf{k}}^2)$ has the d -wave symmetry and is effective only for quasiparticle energies $\xi_{\mathbf{k}} = \varepsilon_{\mathbf{k}} - \varepsilon_F$ smaller than the “Debye energy” ε_D . The latter is understood as a characteristic energy of intermediate (Froelich) boson, and in what follows we suppose the condition $\varepsilon_D < \mu$ to hold and a BCS-shell to exist (the alternative $\mu < \varepsilon_D$, possible for underdoped HTSC systems, will be considered elsewhere). The impurity perturbation V_L expresses the shift of on-site electronic energy on a random dopant site $\mathbf{p}$, where the negative sign takes an explicit account of carrier attraction to the ionized dopant and, for simplicity, we consider this perturbation localized on a single site. With usual BCS ansatz: $c_{-\mathbf{k},\downarrow}c_{\mathbf{k},\uparrow} = \langle c_{-\mathbf{k},\downarrow}c_{\mathbf{k},\uparrow} \rangle + \varphi_{\mathbf{k}}$, and in neglect of quadratic terms in pair fluctuations $\varphi_{\mathbf{k}}$, Eq. 1 leads to a bilinear form for $H' = H - \mu N$:

$$H' = \sum_{\mathbf{k}} \left[\sum_{\sigma} \xi_{\mathbf{k}} c_{\mathbf{k},\sigma}^\dagger c_{\mathbf{k},\sigma} - (\Delta_{\mathbf{k}} c_{-\mathbf{k},\downarrow} c_{\mathbf{k},\uparrow} + h.c.) - \frac{V_L}{N} \sum_{\mathbf{p}, \mathbf{k}', \sigma} e^{-i(\mathbf{k}' - \mathbf{k}) \cdot \mathbf{p}} c_{\mathbf{k}', \sigma}^\dagger c_{\mathbf{k}, \sigma} \right]. \quad (2)$$

Here the gap function is defined by the self-consistency relation

$$\Delta_{\mathbf{k}} = \frac{V\gamma_{\mathbf{k}}}{N} \sum_{\mathbf{k}'} \gamma_{\mathbf{k}'} \langle c_{\mathbf{k}',\uparrow} c_{-\mathbf{k}',\downarrow} \rangle, \quad (3)$$

extending the common BCS gap equation to the d -wave case. A non-uniform system can be treated within the formalism used formerly for impurity problems in SC [14],[19], passing to the Nambu spinors $\psi_{\mathbf{k}}^\dagger = (c_{\mathbf{k},\uparrow}^\dagger, c_{-\mathbf{k},\downarrow})$ and $\psi_{\mathbf{k}}$, and defining the Fourier transformed matrix Green function (GF)

$$\widehat{G}_{\mathbf{k},\mathbf{k}'}(\varepsilon) \equiv \ll \psi_{\mathbf{k}} | \psi_{\mathbf{k}'}^\dagger \gg_\varepsilon = \int_{-\infty}^0 e^{i(\varepsilon - i0)t} \langle \{ \psi_{\mathbf{k}}(t), \psi_{\mathbf{k}'}^\dagger \} \rangle dt. \quad (4)$$

Here $\widehat{A}$ denotes a 2×2 matrix in Nambu indices, $\langle \dots \rangle$ is the quantum statistical average, and $\{a(t), b(0)\}$ the anticommutator of Heisenberg operators. In the GF's below we omit their explicit dependence on energy ε but distinguish between their diagonal and non-diagonal forms in Nambu (N) and momentum (M) indices. Then, applying the Heisenberg equation of motion (EM) $i\hbar \partial \psi_{\mathbf{k}} / \partial t = [H', \psi_{\mathbf{k}}]$ in Eq. 4, we arrive at the Dyson's type EM for SPGF's:

$$\widehat{G}_{\mathbf{k},\mathbf{k}'} = \widehat{G}_{\mathbf{k}}^{(0)} \delta_{\mathbf{k},\mathbf{k}'} - \widehat{G}_{\mathbf{k}}^{(0)} \widehat{V} \sum_{\mathbf{p}, \mathbf{k}''} e^{i(\mathbf{k} - \mathbf{k}'') \cdot \mathbf{p}} \widehat{G}_{\mathbf{k}'', \mathbf{k}'} \quad (5)$$

³So, we do not take into account next neighbor hoppings.

where the non-perturbed SPGF $\hat{G}_{\mathbf{k}}^{(0)} = (\varepsilon - \xi_{\mathbf{k}}\hat{\tau}_3 - \Delta_{\mathbf{k}}\hat{\tau}_1 + i0)^{-1}$, and the scattering matrix $\hat{V} = V_L\hat{\tau}_3$ include the Pauli matrices $\hat{\tau}_i$.

For a disordered system, the relevant (observable) characteristics are described by the so-called self-averaging GF's, whose values for all particular realizations of disorder turn practically non-random, equal to those averaged over disorder [26]. The most important example of such a function is the M-diagonal SPGF, $\hat{G}_{\mathbf{k}} \equiv \hat{G}_{\mathbf{k},\mathbf{k}}$. The general solution for Eq. 5 in this case can be written (see Appendix E) as

$$\hat{G}_{\mathbf{k}} = \left\{ \left[\hat{G}_{\mathbf{k}}^{(0)} \right]^{-1} - \hat{\Sigma}_{\mathbf{k}} \right\}^{-1}, \quad (6)$$

where the self-energy matrix $\hat{\Sigma}_{\mathbf{k}}$ is given by the so-called fully renormalized group expansion (GE) [27], [28],[14],[19]

$$\begin{aligned} \hat{\Sigma}_{\mathbf{k}} = & -c\hat{V} \left[1 + \hat{G}\hat{V} \right]^{-1} \times \\ & \times \left\{ 1 + c \sum_{\mathbf{n} \neq 0} \left[\hat{A}_{0\mathbf{n}} e^{-i\mathbf{k} \cdot \mathbf{n}} + \hat{A}_{0\mathbf{n}} \hat{A}_{\mathbf{n}0} \right] \left[1 - \hat{A}_{0\mathbf{n}} \hat{A}_{\mathbf{n}0} \right]^{-1} + \dots \right\}. \end{aligned} \quad (7)$$

Here the integrated SPGF matrix $\hat{G} = N^{-1} \sum_{\mathbf{k}} \hat{G}_{\mathbf{k}}$, and the matrices $\hat{A}_{0\mathbf{n}}$ of indirect interaction between scatterers at sites 0 and $\mathbf{n}$ are

$$\hat{A}_{0\mathbf{n}} = -\hat{V} \sum_{\mathbf{k}' \neq \mathbf{k}} e^{i\mathbf{k}' \cdot \mathbf{n}} \hat{G}_{\mathbf{k}'} \left[1 + \hat{G}\hat{V} \right]^{-1}. \quad (8)$$

The restriction to $\mathbf{k}' \neq \mathbf{k}$ at single summation in $\hat{A}_{0\mathbf{n}}$ should be complemented by $\mathbf{k}'' \neq \mathbf{k}, \mathbf{k}'$ at double summation in the product $\hat{A}_{0\mathbf{n}} \hat{A}_{\mathbf{n}0}$, but such restrictions can be already ignored in $\hat{A}_{0\mathbf{n}} \hat{A}_{0\mathbf{n}} \hat{A}_{\mathbf{n}0}$ and higher degree terms [27], resulting from expansion of the r.h.s. of Eq. 7.

Many observable characteristics of SC state follow from GF's, using the spectral theorem representation

$$\langle ab \rangle = \int_{-\infty}^{\infty} \frac{d\varepsilon}{e^{\beta(\varepsilon - \mu)} + 1} \text{Im} \ll b|a \gg_{\varepsilon}, \quad (9)$$

where the chemical potential μ is defined by the overall electronic concentration

$$c = \frac{1}{N} \sum_{\mathbf{k}} \int_{-\infty}^{\infty} \frac{d\varepsilon}{e^{\beta(\varepsilon - \mu)} + 1} \text{Im Tr} \hat{\tau}_3 \hat{G}_{\mathbf{k}}. \quad (10)$$

On the other hand, c is just the concentration of dopant centers: $c = N^{-1} \sum_{\mathbf{p}} 1$, which give rise to carrier scattering, and the *carrier* concentration only gets close to (but never exceeds) c in the regime of doped metal, for c above a certain metallization threshold c_0 (for quasi-2D dispersed $\varepsilon_{\mathbf{k}}$, it is $c_0 \sim \exp(-\pi W/4V_L) \ll 1$ [19]). At this condition, the self-consistency implied by Eq. 10 is not necessary,

and a good approximation⁴ for chemical potential is $\mu \approx 3cW/4$ (see Appendix A). Then the gap equation, Eq. 3, presents as

$$\Delta_{\mathbf{k}} = \frac{V\gamma_{\mathbf{k}}}{2N} \sum_{\mathbf{k}'} \gamma_{\mathbf{k}'} \int_{-\infty}^{\infty} \frac{d\varepsilon}{e^{\beta(\varepsilon-\mu)} + 1} \text{Im Tr} \hat{\tau}_1 \hat{G}_{\mathbf{k}'}, \quad (11)$$

and its solution discussed in Appendix C for the uniform case ($V_L = 0$) is simply $\Delta_{\mathbf{k}} = \Delta\gamma_{\mathbf{k}}$, with the ratio $r = 2\Delta/k_B T_c$ being $e^{1/3}$ times the s -wave BCS value $r_{\text{BCS}} \approx 3.52$.

Another important self-averaging quantity is the integrated SPGF matrix $\hat{G}$ itself, since the density of states $\rho(\varepsilon)$ is just

$$\rho(\varepsilon) = \frac{1}{\pi} \text{Im Tr} \hat{G}. \quad (12)$$

For a non-perturbed system, $V_L \rightarrow 0$, $\hat{G} \rightarrow \hat{G}^{(0)} = N^{-1} \sum_{\mathbf{k}} \hat{G}_{\mathbf{k}}^{(0)}$, and calculation of the imaginary part of $\hat{G}^{(0)}$ within the nodal point approximation (Appendix B) leads to the standard d -wave density of states:

$$\rho(\varepsilon) \rightarrow \rho^{(0)}(\varepsilon) = \frac{1}{\pi} \text{Im Tr} \hat{G}^{(0)} = \frac{2\varepsilon\rho_0}{\Delta} \arcsin \left[\min \left(1, \frac{\Delta}{\varepsilon} \right) \right], \quad (13)$$

where $\rho_0 \approx 4/(\pi W)$ is the normal Fermi density of states of doped (quasi-2D) metal. Respectively, the real part of $\hat{G}^{(0)}$ is

$$\text{Re} \hat{G}^{(0)} = \varepsilon\rho_0 \left[\frac{W}{\mu(W-\mu)} - \frac{\pi}{\Delta} \theta(\Delta - \varepsilon) \text{arccosh} \frac{\Delta}{\varepsilon} \right]. \quad (14)$$

Then Eqs. 13 and 14 can be unified into a single analytic form:

$$\hat{G}^{(0)} = \varepsilon\rho_0 \left[\frac{W}{\mu(W-\mu)} - \frac{\pi}{\Delta} \left(\text{arccosh} \frac{\Delta}{\varepsilon} - i \frac{\pi}{2} \right) \right], \quad (15)$$

since at $\varepsilon > \Delta$ one has $\text{arccosh}(\Delta/\varepsilon) = i[\pi/2 - \arcsin(\Delta/\varepsilon)]$, thus restoring Eq. 13. But it is just the growth of (real) arccosh term at $\varepsilon < \Delta$ that permits existence of a low-energy ($\varepsilon_{\text{res}} \ll \Delta$) resonance feature in $\text{Re}(1 + \hat{G}\hat{V})^{-1}$, and hence in $\rho(\varepsilon)$. Such a resonance was formerly discussed for a d -wave SC with low enough concentration c (so that $\hat{G} \approx \hat{G}^{(0)}$) of “foreign” impurities producing strong enough perturbation V_L [14], and it is similar to the known low-frequency resonance by heavy impurities in acoustic phonon spectra [29]. However, in the situation of our interest here, when both V_L and c are not small, $\hat{G}$ can be essentially modified compared to $\hat{G}^{(0)}$ and this is expressed in a very complicate way by Eq. 7. To simplify the task, certain self-consistent procedures, like the CPA method, quite useful in the theory of normal metals [30], can be employed. Similar approach was formerly proposed for an s -wave SC doped system [19], and here we begin with the analysis of a self-consistent solution for Eq. 5 in the d -wave case.

⁴This approximation is actually justified by the fact that for $c > c_0$ the Fermi level ε_F of metallic phase is well higher than the conduction band edge, and one can hardly suppose existence of local pairs and related inequality $\mu < \varepsilon_F$ at these concentrations. Therefore, in what follows we do not distinguish between μ and ε_F .

3 Uniform doping effects in self-consistent approach

If the GE series, Eq. 7, is restricted to its first term, the self-energy matrix $\widehat{\Sigma}_{\mathbf{k}}$ turns in fact independent of $\mathbf{k}$:

$$\widehat{\Sigma}_{\mathbf{k}} \rightarrow \widehat{\Sigma} = -c\widehat{V} \left[1 + \widehat{G}\widehat{V} \right]^{-1}, \quad (16)$$

and substitution of Eq. 16 into Eq. 6 defines the self-consistent approximation $\widehat{G}_{\mathbf{k}}^{(sc)}$ for M-diagonal SPGF:

$$\widehat{G}_{\mathbf{k}}^{(sc)} = \left\{ \left[\widehat{G}_{\mathbf{k}}^{(0)} \right]^{-1} - \widehat{\Sigma}^{(sc)} \right\}^{-1}, \quad (17)$$

$$\widehat{\Sigma}^{(sc)} = -c\widehat{V} \left[1 + \widehat{G}^{(sc)}\widehat{V} \right]^{-1}, \quad (18)$$

$$\widehat{G}^{(sc)} = \frac{1}{N} \sum_{\mathbf{k}} \widehat{G}_{\mathbf{k}}^{(sc)}. \quad (19)$$

To solve this system, we first parametrize the self-energy matrix, Eq. 18:

$$\widehat{\Sigma}^{(sc)} = \Sigma_0 + \Sigma_1 \widehat{\tau}_1 + \Sigma_3 \widehat{\tau}_3, \quad (20)$$

Σ_i being some complex-valued functions of energy. Then integration in Eq.19 within the nodal point approximation (Appendix D) results in

$$\widehat{G}^{(sc)} = G_0 + G_1 \widehat{\tau}_1 + G_3 \widehat{\tau}_3 \quad (21)$$

with the coefficients

$$G_0 = (\varepsilon - \Sigma_0) \rho_0 \left[-\frac{\pi}{2\Delta} \left(\operatorname{arccosh} \frac{\Delta + \Sigma_1}{\varepsilon - \Sigma_0} + \operatorname{arccosh} \frac{\Delta - \Sigma_1}{\varepsilon - \Sigma_0} - i\pi \right) + \right. \quad (22)$$

$$\left. + \frac{W}{\mu(W - \mu)} \right],$$

$$G_1 = \Sigma_1 \rho_0 \left[-\frac{2i\pi}{\sqrt{(\varepsilon - \Sigma_0)^2 - (\Delta + \Sigma_1)^2} + \sqrt{(\varepsilon - \Sigma_0)^2 - (\Delta - \Sigma_1)^2}} + \right. \quad (23)$$

$$\left. + \frac{W}{\mu(W - \mu)} \right],$$

$$G_3 = \rho_0 \left[\ln \frac{\mu}{W - \mu} + 2\Sigma_3 \frac{(\varepsilon - \Sigma_0)^2 - \Delta^2/3 - \Sigma_1^2}{\varepsilon_D^3} \right]. \quad (24)$$

Substituting Eq. 21 into Eq. 18, we arrive at

$$\widehat{\Sigma}^{(sc)} = \frac{cV_L [V_L (G_0 + G_1 \widehat{\tau}_1) - (1 + V_L G_3) \widehat{\tau}_3]}{(1 + V_L G_3)^2 - V_L^2 (G_0^2 - G_1^2)}. \quad (25)$$

Comparing Eqs. 25, and 22, 23, 24 with Eq. 20, we immediately conclude that $\Sigma_1 = G_1 = 0$, or that $\widehat{\Sigma}^{(sc)}$ is in fact *N-diagonal*, which is extremely important. Physically, this means that (within the self-consistent, linear in c approximation) the scattering by dopants does not influence the d -wave order parameter, and this can be directly related to the fact that the s -symmetry of impurity perturbation V_L is orthogonal to the d -symmetry of SC pairing V . It also applies to more realistic models of dopant perturbation in HTSC (e.g. with plaquette- or dumbbell-like anisotropy [31]), as far as their symmetries do not coincide with that of the order parameter. Complications arise when they do coincide, as was found for isotropic perturbation on s -wave order with all three Σ_i being non-zero [19], hence the apparently “harder” d -wave system turns in fact “easier”!

Using the fact that $\Sigma_1 = 0$ and the relation $\cosh(x + i\pi/2) = \sin x$, Eq. 22 is brought to a very simple form:

$$\frac{\Delta}{\varepsilon - \Sigma_0} = \sin \left(\alpha - \frac{G_0}{\pi \rho_0} \frac{\Delta}{\varepsilon - \Sigma_0} \right), \quad (26)$$

with $\alpha = W\Delta/[\pi\mu(W - \mu)] \ll 1$, while the same comparison for the two non-zero components of $\widehat{\Sigma}^{(sc)}$: Σ_0 and Σ_3 , gives:

$$\Sigma_0 \left[(1 + V_L G_3)^2 - V_L^2 G_0^2 \right] = cV_L^2 G_0, \quad (27)$$

$$\Sigma_3 \left[(1 + V_L G_3)^2 - V_L^2 G_0^2 \right] = -cV_L (1 + V_L G_3). \quad (28)$$

From Eq. 28 we estimate $|\Sigma_3| \sim cV_L$, hence within the relevant energy region $|\varepsilon| \ll \varepsilon_D$, the function G_3 from Eq. 24 is reasonably well approximated by a (negative) constant $g_3 = \rho_0 \ln[\mu/(W - \mu)]$. Then Eq. 27 turns quadratic for G_0 :

$$G_0^2 + \frac{c}{\Sigma_0} G_0 - \left(\frac{1}{\widetilde{V}} \right)^2 = 0, \quad (29)$$

with $\widetilde{V} = V_L/(1 + V_L g_3) \approx V_L \ln(1/c_0)/\ln(3c/4c_0)$. The system, Eqs. 26, 29, fully defines the self-energy Σ_0 and other uniform physical properties of a disordered d -wave system, and its solution can be found (in principle numerically) within the whole relevant energy range. It turns especially simple if $|\Sigma_0| \ll c\widetilde{V}$ (this proves to hold at least for $\varepsilon \ll \varepsilon_{res}$), then the proper solution to Eq. 29 is: $G_0 \approx \Sigma_0/c\widetilde{V}^2$, and from Eq. 26 we obtain the following equation for a single important function Σ_0 :

$$\frac{\Delta}{\varepsilon - \Sigma_0} = \sin \left(\alpha - \frac{\beta \Sigma_0}{\varepsilon - \Sigma_0} \right) \quad (30)$$

with $\beta = \Delta/[\pi c \tilde{V}^2 \rho_0] \ll 1$. It defines the self-consistent density of states

$$\rho^{(sc)}(\varepsilon) = \frac{1}{\pi} \text{Im Tr} \hat{G}^{(sc)}(\varepsilon) = \frac{2 \text{Im} \Sigma_0(\varepsilon)}{\pi c \tilde{V}^2}, \quad (31)$$

at lowest energies. This approach results free of infrared logarithmic divergencies, appearing in the integrals of perturbation theory [32], and thus permits to avoid applying heavy field theory methods for white-noise scattering potential [15], whose adequacy to the case of discrete random dopants is not clear.

The exact value of the density of states at the very center of the gap, $\rho(0) = \rho(\varepsilon \rightarrow 0)$, is also of a particular interest in view of the known claim about existence of a non-zero “universal” value $\rho(0) \sim c/\ln(1/c)$ if V_L is sufficiently strong [12], [17]. However, we conclude from Eq. 30 that in the limit $\varepsilon \rightarrow 0$:

$$\Sigma_0 \rightarrow \varepsilon \left[1 + i \frac{\beta}{\ln(2\Delta/\beta|\varepsilon|)} \right],$$

and hence the self-consistent density of states at $\varepsilon \rightarrow 0$:

$$\rho^{(sc)}(\varepsilon) \rightarrow \frac{4\beta^2 \rho^{(0)}(\varepsilon)}{\pi \ln(2\Delta/\beta|\varepsilon|)}, \quad (32)$$

vanishes even faster than the non-perturbed function $\rho^{(0)}(\varepsilon)$, Eq. 13. This produces a certain narrow “quasi-gap” (not to be confused with the pseudo-gap observed at $T > T_c$ in the underdoped regime) around the center. For comparison, the estimated $\rho(\varepsilon)$ from the two first terms of Eq. 7 tends to zero linearly in ε with corrections $\sim \varepsilon^2$ [14], while the field-theoretical analysis [15] predicts $\rho(\varepsilon) \rightarrow \varepsilon^\omega$, with the non-universal exponent being (in our notations) $\omega = \tanh \ln \sqrt{\pi^2 \Delta W / 2cV_L^2}$, that is always < 1 and even not excluding < 0 .

The discrepancy between our results and the before mentioned “universal” behavior originates in the improper use of unitary limit $V_L \rightarrow \infty$ at neglect of the $1 + V_L G_3$ term in Eq. 27, leading to the relation $\Sigma_0 = -c/G_0$. But the true limiting relation is inverse: $\Sigma_0 = c\tilde{V}^2 G_0$, with $\tilde{V}$ *finite* for $V_L \rightarrow \infty$, and also the unitary limit fails at any⁵ finite V_L when $\varepsilon \rightarrow 0$. Finally, the existing experimental data do not confirm the “universal” $\rho(0)$ value, but seem to favor the conclusion about existence of a strong low-energy resonance in $\rho(\varepsilon)$ [11], with possible quasi-gap at the very center [33], though experimental observations at such low energies of course need extremely low temperatures.

Note however that the self-consistent treatment of the low-energy resonance, at $\varepsilon_{res} \sim \Delta \ln(3c/4c_0)/(\pi \ln 2\pi)$ for the case of “own” impurities (Fig. ??), requires already solution of the full system, Eqs. 26, 29, and, in view of a probable underestimate of this hump (like that in normal systems [28],[30]), it should be better described by the exact GE, Eq. 7.

The obtained $\hat{\Sigma}^{(sc)}$ can be in principle directly inserted in Eq. 17, in order to use the resulting $\hat{G}_k^{(sc)}$ for correction of the gap equation, Eq. 11. However, at important there quasiparticle energies $\xi_k \sim \varepsilon_D$, renormalization effects are negligible, and thus Δ remains well approximated by the result of Appendix C.

⁵Unless the special case $1/\tilde{V} = 0$ corresponding to $c \approx 4c_0/3$, while the actual consideration is for $c \gg c_0$.

4 Non-uniform effects

The SPGF's, considered in the previous section, describe the uniform self-averaging characteristics of SC state. The next important question is the behavior of fluctuations of the order parameter (both its amplitude and phase) in an inhomogeneous system, which should be closely related to the breakdown of superconductivity in the overdoped regime. A strong local suppression of d -wave order close to a single “foreign” impurity was predicted theoretically [14] and observed experimentally [11]. In the general case of finite concentration of scatterers, the local d -wave order can be characterized by the operator

$$\Omega_{\mathbf{n}} = \frac{V}{N} \sum_{\mathbf{k}, \mathbf{k}'} \gamma_{\mathbf{k}} e^{i(\mathbf{k}-\mathbf{k}') \cdot \mathbf{n}} c_{-\mathbf{k}, \downarrow} c_{\mathbf{k}', \uparrow}, \quad (33)$$

such that its mean value (generally complex) defines the uniform gap parameter: $N^{-1} \sum_{\mathbf{n}} \langle \Omega_{\mathbf{n}} \rangle = N^{-1} \sum_{\mathbf{k}} \gamma_{\mathbf{k}} \Delta_{\mathbf{k}} = \Delta$ [14]. On the other hand, it is natural to characterize local fluctuations of order parameter by the mean squared dispersion of $\Omega_{\mathbf{n}}$ (identified with the dispersion of gap parameter):

$$\delta^2 = \frac{1}{N} \sum_{\mathbf{n}} \left(\langle \Omega_{\mathbf{n}}^2 \rangle - \langle \Omega_{\mathbf{n}} \rangle^2 \right). \quad (34)$$

Using Eq. 33, we write

$$\begin{aligned} \delta^2 = \frac{V^2}{N^3} \sum_{\mathbf{n}} \sum_{\mathbf{k}_1, \mathbf{k}_2, \mathbf{k}_3, \mathbf{k}_4} e^{i(\mathbf{k}_1 + \mathbf{k}_2 - \mathbf{k}_3 - \mathbf{k}_4) \cdot \mathbf{n}} \gamma_{\mathbf{k}_1} \gamma_{\mathbf{k}_2} [\langle c_{-\mathbf{k}_1, \downarrow} c_{\mathbf{k}_3, \uparrow} c_{-\mathbf{k}_2, \downarrow} c_{\mathbf{k}_4, \uparrow} \rangle - \\ - \langle c_{-\mathbf{k}_1, \downarrow} c_{\mathbf{k}_3, \uparrow} \rangle \langle c_{-\mathbf{k}_2, \downarrow} c_{\mathbf{k}_4, \uparrow} \rangle], \end{aligned} \quad (35)$$

or, summing up in $\mathbf{n}$ to close the sum of 4 momenta, and using the spectral representation, Eq. 9, for $T = 0$:

$$\begin{aligned} \delta^2 = \frac{V^2}{N^2} \sum_{\mathbf{k}_1, \mathbf{k}_2, \mathbf{q}} \gamma_{\mathbf{k}_1} \gamma_{\mathbf{k}_2} \left[\int_0^\infty d\varepsilon \text{Im} \ll c_{-\mathbf{k}_1, \downarrow} c_{\mathbf{k}_2, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg - \right. \\ \left. - \int_0^\infty d\varepsilon \text{Im} \ll c_{-\mathbf{k}_1, \downarrow} | c_{\mathbf{k}_2, \uparrow} \gg \int_0^\infty d\varepsilon \text{Im} \ll c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} | c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \right]. \end{aligned} \quad (36)$$

Here, besides the before used SPGF's, the TPGF $\ll c_{-\mathbf{k}_1, \downarrow} c_{\mathbf{k}_2, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg$ appears. An explicit calculation of this function for non-perturbed ($V_L = 0$) SC system (see Appendix E) gives the following result

$$\ll c_{-\mathbf{k}_1, \downarrow} c_{\mathbf{k}_2, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg = \delta_{0, \mathbf{q}} \frac{(4\varepsilon \Delta_{\mathbf{k}_1} \Delta_{\mathbf{k}_2} + \dots)}{(\varepsilon^2 - E_{\mathbf{k}_1}^2 - E_{\mathbf{k}_2}^2)^2 - 4E_{\mathbf{k}_1}^2 E_{\mathbf{k}_2}^2}. \quad (37)$$

Here $E_{\mathbf{k}}^2 = \xi_{\mathbf{k}}^2 + \Delta_{\mathbf{k}}^2$, and three other terms in numerator are not mutually odd in $\gamma_{\mathbf{k}_1}$ and $\gamma_{\mathbf{k}_2}$ and thus do not contribute into δ^2 . Then, it is easy to see that the

resulting contribution into Eq. 36 from M-diagonal ($\mathbf{q} = 0$) and N-non-diagonal TPGF's by Eq. 37 exactly cancels with that from SPGF's, which confirms uniformity of d -wave order in this case. The most important contribution to δ^2 at $V_L \neq 0$ comes from two consecutive scattering processes in the l.h.s. of an N- and M-non-diagonal ($\mathbf{q} \neq 0$) TPGF, first $c_{-\mathbf{k}_1, \downarrow} c_{\mathbf{k}_2, \uparrow} \rightarrow c_{-\mathbf{k}_1 + \mathbf{q}, \downarrow} c_{\mathbf{k}_2, \uparrow}$ and then $c_{-\mathbf{k}_1 + \mathbf{q}, \downarrow} c_{\mathbf{k}_2, \uparrow} \rightarrow c_{-\mathbf{k}_1 + \mathbf{q}, \downarrow} c_{\mathbf{k}_2 - \mathbf{q}, \uparrow}$ (or vice versa, Fig. ??), on the same scattering center $\mathbf{p}$. It is linear in c , while the contribution from SPGF's in this order, $-2\Delta V \int_0^\infty d\varepsilon \text{Im Tr} \hat{\tau}_1 \hat{\Sigma}$, is zero, accordingly to N-diagonal form of $\hat{\Sigma}$ established in previous Section. Hence we generally estimate the gap dispersion to grow with c as $|\delta| = \Delta \sqrt{c/c_1}$, where $c_1 \sim (V/V_L)^2$ defines the upper critical concentration for SC at $T = 0$.

A more detailed analysis, resolving amplitude and phase fluctuations, can be done in a similar way, but considering separately two operators:

$$\Omega_{\mathbf{n},+} = \frac{\Omega_{\mathbf{n}} + \Omega_{\mathbf{n}}^+}{2}, \quad \text{and} \quad \Omega_{\mathbf{n},-} = \frac{\Omega_{\mathbf{n}} - \Omega_{\mathbf{n}}^+}{2i},$$

such that their mean values $\langle \Omega_{\mathbf{n},\pm} \rangle$ lead to real and imaginary parts of the order parameter, and constructing the corresponding dispersions:

$$\delta_{\pm}^2 = \frac{1}{N} \sum_{\mathbf{n}} \left(\langle \Omega_{\mathbf{n},\pm}^2 \rangle - \langle \Omega_{\mathbf{n},\pm} \rangle^2 \right).$$

This approach should be particularly important at extension of the theory to finite temperatures, in order to establish the dominating type of fluctuations due to the static disorder, responsible for breakdown of SC order at $T = T_c$, and its possible role in the persistence of a pseudogap in the density of states ρ at $T > T_c$.

5 Conclusions

The above presented analysis shows that the disordered structure of doped HTSC systems is crucial for many of their characteristic properties and for existence of SC order itself. The interplay between doping and disorder effects can be briefly resumed as follows. Superconductivity onsets with the metallization of the system, at critical concentration $c \sim c_0$ resulted from the competition between kinetic energy of charge carriers in regular lattice and their attraction to random dopant centers. The uniform d -wave order parameter Δ develops with growing number of charge carriers as $\Delta \sim \sqrt{c}$ [6] and saturates at certain optimum doping $c_{opt} \sim \varepsilon_D/W$, when the relation $\mu > \varepsilon_D$ becomes to hold. With further growing c , the increasing local fluctuations of Δ bring it to collapse at some upper critical concentration $c_1 \sim (V/V_L)^2$, resulted from the competition between pairing and scattering potentials. This picture is quantitatively satisfied with a very natural choice of parameters $W \sim 2$ eV, $V_L \sim 0.5$ eV, $V \sim 0.22$ eV, $\varepsilon_D \sim 0.2$ eV, giving plausible estimates: $c_0 \sim 5\%$, $c_{opt} \sim 15\%$, $T_{c,max} \sim 100\text{K}$, $c_1 \sim 20\%$. The forthcoming work should also specify such important moments, left beyond the scope of this consideration, as the disorder

effects on the cusp of density of states $\rho(\varepsilon)$ at $\varepsilon = \Delta$, the matching conditions between the self-consistent and GE descriptions of SPGF, the exact numerical coefficient for the critical value c_1 , etc. And, of course, it is of principal interest to extend the present self-consistent treatment to the case of finite temperatures up to T_c , in order to obtain a quantitative estimate for the bell-like $T_c(c)$ shape, and further to $T > T_c$, to study the role of doping disorder vs d -wave SC coupling in the formation and subsequent merging (at $c \sim c_{opt}$) of the pseudogap in normal density of states.

This work was supported in parts by Portuguese Program PRAXIS XXI under the Grant 2/2.1/FIS/302/94, by NATO Program OUTREACH under the Grant CP/UN/19/C/2000/PO, and by Swiss National Science Foundation (SCOPES Project 7UKPJ062150.00/1). One of us (V.M.L.) expresses his gratitude for a warm hospitality he felt at visiting Centro de Física do Porto.

6 Appendix A

For the normal phase, we consider the dispersion law $\varepsilon_{\mathbf{k}} = 4t - 2t(\cos ak_x + \cos ak_y)$ and relate the dopant concentration c to the number (per unit cell) of occupied states below μ :

$$\begin{aligned} c &= \frac{2a^2}{(2\pi)^2} \int_{\varepsilon_{\mathbf{k}} \leq \mu} d\mathbf{k} = \frac{2a^2}{\pi^2} \int_0^{\arccos(1-4\mu/W)} dk_x \int_0^{\arccos(2-4\mu/W-\cos ak_x)} dk_y = \\ &= \frac{2}{\pi^2} \int_{1-4\mu/W}^1 \frac{du}{\sqrt{1-u^2}} \int_{2-4\mu/W-u}^1 \frac{dv}{\sqrt{1-v^2}} = \frac{2}{\pi^2} F\left(\frac{4\mu}{W}\right). \end{aligned} \quad (38)$$

Here the dependence of the integral

$$F(x) = \int_{1-x}^1 \frac{\arccos(2-x-u)}{\sqrt{1-u^2}} du$$

is very well approximated by a simple linear function $F(x) \approx 5x/3$ in the whole physically important range $0 \leq x = 4\mu/W \leq x_{max}$ (where $x_{max} \approx 0.6$ corresponds to $\mu_{max} \approx 0.15W$ at maximum physical doping $c_{max} \approx 0.2$). Then we readily arrive at the estimate

$$\mu \approx \frac{3\pi^2}{40} cW \approx \frac{3cW}{4},$$

cited above.

7 Appendix B

For the uniform SC system with d -wave gap, we perform integration over the Brillouin zone with the parametrization: $\mathbf{k} - \mathbf{k}_i = a^{-1}(\rho_0 \xi \mathbf{e}_i + \Delta^{-1} \eta \mathbf{e}_i \times \mathbf{e}_z)$, $\mathbf{e}_i =$

$(\pm 1/\sqrt{2}, \pm 1/\sqrt{2}, 0)$, $\mathbf{e}_z = (0, 0, 1)$, near 4 nodal points $\mathbf{k}_i = \arccos(1 - \mu/W) \mathbf{e}_i$ of the gap function $\Delta_{\mathbf{k}} = \Delta \gamma_{\mathbf{k}}^{(d)}$. This integration for $\hat{G}^{(0)}$ turns into

$$\begin{aligned} \hat{G}^{(0)} = \frac{1}{N} \sum_{\mathbf{k}} \hat{G}_{\mathbf{k}}^{(0)} = \rho_0 \left[\frac{1}{2\Delta} \int_{-\Delta}^{\Delta} d\eta \int_{-\varepsilon_D}^{\varepsilon_D} d\xi \hat{g}(\varepsilon, \xi, \eta) + \right. \\ \left. + \int_{-\mu}^{-\varepsilon_D} d\xi \hat{g}(\varepsilon, \xi, 0) + \int_{\varepsilon_D}^{W-\mu} d\xi \hat{g}(\varepsilon, \xi, 0) \right], \end{aligned} \quad (39)$$

where we have defined the matrix function

$$\hat{g}(\varepsilon, \xi, \eta) = (\varepsilon - \xi \hat{\tau}_3 - \eta \hat{\tau}_1)^{-1} = \frac{\varepsilon + \xi \hat{\tau}_3 + \eta \hat{\tau}_1}{\varepsilon^2 - \xi^2 - \eta^2}.$$

The integration in ξ (normal to the Fermi surface) in Eq. 39 treats the BCS shell, $[-\varepsilon_D, \varepsilon_D]$, separately from the out-of-shell segments, $[-\mu, -\varepsilon_D]$ and $[\varepsilon_D, W - \mu]$, where the gap parameter Δ turns zero (together with $\gamma_{\mathbf{k}}$) and no integration in $\eta = \Delta \gamma_{\mathbf{k}}$ is needed. Eq. 39 permits to define explicitly the coefficient functions g_i in the general form $\hat{G}^{(0)} = g_0 + g_1 \hat{\tau}_1 + g_3 \hat{\tau}_3$. Let us denote $z^2 = \varepsilon^2 - \eta^2$, then the shell contribution to g_0 result from the integral:

$$\int_{-\varepsilon_D}^{\varepsilon_D} \frac{d\xi}{z^2 - \xi^2} = \frac{2}{z} \left(\operatorname{arctanh} \frac{z}{\varepsilon_D} + i\pi \right) \approx \frac{2}{\varepsilon_D} + \frac{2i\pi}{z}, \quad (40)$$

which is followed for its last term by:

$$\int_{-\Delta}^{\Delta} \frac{d\eta}{\sqrt{\varepsilon^2 - \eta^2}} = 2 \arccos \frac{\Delta}{\varepsilon}. \quad (41)$$

The out-of-shell contributions are:

$$\int_{-\mu}^{-\varepsilon_D} \frac{d\xi}{\varepsilon^2 - \xi^2} = \frac{1}{\varepsilon} \left(\operatorname{arctanh} \frac{\varepsilon}{\mu} - \operatorname{arctanh} \frac{\varepsilon}{\varepsilon_D} \right) \approx \frac{1}{\mu} - \frac{1}{\varepsilon_D} \quad (42)$$

and

$$\int_{\varepsilon_D}^{W-\mu} \frac{d\xi}{\varepsilon^2 - \xi^2} \approx \frac{1}{W - \mu} - \frac{1}{\varepsilon_D}. \quad (43)$$

To find g_1 and g_3 , we use the evident equalities

$$\int_{-\varepsilon_D}^{\varepsilon_D} \frac{\xi d\xi}{z^2 - \xi^2} = \int_{-1}^1 \eta d\eta = 0,$$

and:

$$\int_{-\mu}^{-\varepsilon_D} \frac{\xi d\xi}{\varepsilon^2 - \xi^2} + \int_{\varepsilon_D}^{W-\mu} \frac{\xi d\xi}{\varepsilon^2 - \xi^2} = \frac{1}{2} \ln \frac{\mu^2 - \varepsilon^2}{(W - \mu)^2 - \varepsilon^2} \approx \ln \frac{\mu}{W - \mu}. \quad (44)$$

Summing up Eqs. 40-44, we obtain

$$g_0 = \varepsilon \rho_0 \left[\frac{W}{\mu(W - \mu)} - \frac{\pi}{\Delta} \left(\operatorname{arccosh} \frac{\Delta}{\varepsilon} - \frac{i\pi}{2} \right) \right]$$

in accordance with Eq. 15, $g_1 = 0$, and $g_3 = \rho_0 \ln[\mu/(W - \mu)]$.

8 Appendix C

The gap equation, Eq. 11, for uniform ($V_L = 0$) d -wave system at $T = 0$ transforms into:

$$\frac{1}{\lambda} = \frac{16}{\pi\Delta^3} \text{Im} \int_0^\Delta \eta^2 d\eta \int_0^{\varepsilon_D} d\xi \int_0^\infty \frac{d\varepsilon}{\varepsilon^2 - \xi^2 - \eta^2 - i0}, \quad (45)$$

with $\lambda = V\rho_0$. The sought quantity is the gap amplitude Δ . On the r.h.s. of Eq. 45 we perform the elementary integration in ε , using the relation $\text{Im} (x - i0)^{-1} = \pi\delta(x)$:

$$\begin{aligned} \frac{16}{\pi} \text{Im} \int_0^\Delta \eta^2 d\eta \int_0^{\varepsilon_D} d\xi \int_0^\infty \frac{d\varepsilon}{\varepsilon^2 - \xi^2 - \eta^2 - i0} &= \\ &= 8 \int_0^\Delta \eta^2 d\eta \int_0^{\varepsilon_D} \frac{d\xi}{\sqrt{\xi^2 + \eta^2}} \end{aligned} \quad (46)$$

Then, integrating out in ξ and passing from η to $y = \hbar\omega_D/\eta$, we present Eq. 46 as

$$\begin{aligned} 8 \left(\frac{\varepsilon_D}{\Delta} \right)^3 \int_{\frac{\varepsilon_D}{\Delta}}^\infty \frac{\text{arcsinh} y \, dy}{y^4} &= \frac{8}{3} \text{arcsinh} \frac{\varepsilon_D}{\Delta} + 4 \frac{\varepsilon_D \sqrt{\varepsilon_D^2 + \Delta^2}}{3\Delta^2} \\ -\frac{4}{3} \left(\frac{\varepsilon_D}{\Delta} \right)^3 \text{arcsinh} \frac{\Delta}{\varepsilon_D} &\approx \frac{8}{3} \left(\ln \frac{2\varepsilon_D}{\Delta} + \frac{1}{3} \right). \end{aligned}$$

The equation for critical temperature T_c , corresponding to $\Delta = 0$, reads in this case

$$\frac{1}{\lambda} = \frac{16}{3\pi} \text{Im} \int_0^{\varepsilon_D} d\xi \tanh \left(\frac{\xi}{2k_B T_c} \right) \int_0^\infty \frac{d\varepsilon}{\varepsilon^2 - \xi^2 - i0} \approx \frac{8}{3} \ln \left(\frac{2\gamma_E \varepsilon_D}{\pi k_B T_c} \right),$$

with the Euler constant $\gamma_E \approx 1.781$. Hence for the d -wave case the effective coupling constant is $\tilde{\lambda} = 8\lambda/3$, that is $8/3$ times the ‘‘Hamiltonian’’ value λ , which can serve as one more explanation for high T_c itself. Also, the ratio $r = 2\Delta/k_B T_c$ results here $\exp(1/3)$ times the common s -wave BCS value $r_s = 2\pi/\gamma_E \approx 3.52$, reaching as high value as $r_d \approx 4.92$. In its turn, this means that, for equal other conditions (say, ρ_0 and V), s -condensate turns out more stable to thermal fluctuations and requires a higher T_c to destroy it than d -condensate. Of course, this is directly related to the absence of gap in the latter case, permitting quasi-particles to exist at any $T < T_c$.

9 Appendix D

Calculation of the self-consistent SPGF $\hat{G}^{(sc)} = G_0 + G_1 \hat{\tau}_1 + G_3 \hat{\tau}_3$ generalizes the scheme of Appendix B:

$$\begin{aligned}\widehat{G}^{(sc)} = \frac{1}{N} \sum_{\mathbf{k}} \widehat{G}_{\mathbf{k}}^{(sc)} = \rho_0 \left[\frac{1}{2\Delta} \int_{-\Delta}^{\Delta} d\eta \int_{-\varepsilon_D}^{\varepsilon_D} d\xi \widehat{g}(\varepsilon - \Sigma_0, \xi + \Sigma_3, \eta + \Sigma_1) + \right. \\ \left. + \int_{-\mu}^{-\varepsilon_D} d\xi \widehat{g}(\varepsilon - \Sigma_0, \xi + \Sigma_3, \Sigma_1) + \int_{\varepsilon_D}^{W-\mu} d\xi \widehat{g}(\varepsilon - \Sigma_0, \xi + \Sigma_3, \Sigma_1) \right].\end{aligned}\quad (47)$$

Next we set $z^2 = (\varepsilon - \Sigma_0)^2 - (\eta + \Sigma_1)^2$ and $z = r + i\gamma$, and pass from ξ to $x = \xi + \Sigma_3$, where Σ_3 can be taken real (as seen e.g. from the final result Eq. 28). Then the analogue to Eq. 40 is:

$$\begin{aligned}\int_{-\varepsilon_D+\Sigma_3}^{\varepsilon_D+\Sigma_3} \frac{dx}{z^2 - x^2} = \frac{1}{2z} \times \\ \times \left\{ \frac{1}{2} \ln \frac{[(\varepsilon_D + \Sigma_3 + r)^2 + \gamma^2]}{[(\varepsilon_D - \Sigma_3 - r)^2 + \gamma^2]} \frac{[(\varepsilon_D - \Sigma_3 + r)^2 + \gamma^2]}{[(\varepsilon_D + \Sigma_3 - r)^2 + \gamma^2]} - \right. \\ \left. + i \left[\arctan \frac{\varepsilon_D + \Sigma_3 + r}{\gamma} + \arctan \frac{\varepsilon_D + \Sigma_3 - r}{\gamma} + \right. \right. \\ \left. \left. + \arctan \frac{\varepsilon_D - \Sigma_3 + r}{\gamma} + \arctan \frac{\varepsilon_D - \Sigma_3 - r}{\gamma} \right] \right\} \approx \\ \approx \frac{2}{\varepsilon_D} - i \frac{\pi + 2\gamma/\varepsilon_D}{z},\end{aligned}\quad (48)$$

where the small term $2\gamma/\varepsilon_D$ can be safely dropped. The next integration, in $y = \eta + \Sigma_1$, is done only on $i\pi/z$ term accordingly to:

$$\int_{-\Delta+\Sigma_1}^{\Delta+\Sigma_1} \frac{dy}{\sqrt{(\varepsilon - \Sigma_0)^2 - y^2}} = \arccos \frac{\Delta + \Sigma_1}{\varepsilon - \Sigma_0} + \arccos \frac{\Delta - \Sigma_1}{\varepsilon - \Sigma_0}, \quad (49)$$

which is relevant for G_0 , supplemented with

$$\begin{aligned}\int_{-\Delta+\Sigma_1}^{\Delta+\Sigma_1} \frac{y dy}{\sqrt{(\varepsilon - \Sigma_0)^2 - y^2}} = \\ = - \frac{4\Delta\Sigma_1}{\sqrt{(\varepsilon - \Sigma_0)^2 - (\Delta + \Sigma_1)^2} + \sqrt{(\varepsilon - \Sigma_0)^2 - (\Delta - \Sigma_1)^2}}\end{aligned}\quad (50)$$

for G_1 . The out-of-shell integration of the mentioned components is much easier, giving:

$$\int_{\varepsilon_D - \Sigma_3}^{\mu - \Sigma_3} \frac{dx}{(\varepsilon - \Sigma_0)^2 - x^2} = \frac{1}{\varepsilon - \Sigma_0} \left(\operatorname{arctanh} \frac{\varepsilon - \Sigma_0}{\mu - \Sigma_3} - \operatorname{arctanh} \frac{\varepsilon - \Sigma_0}{\varepsilon_D - \Sigma_3} \right) \approx$$

$$\approx \frac{1}{\mu - \Sigma_3} - \frac{1}{\varepsilon_D - \Sigma_3}, \quad (51)$$

and

$$\int_{\varepsilon_D - \Sigma_3}^{W - \mu - \Sigma_3} \frac{dx}{(\varepsilon - \Sigma_0)^2 - x^2} \approx \frac{1}{W - \mu - \Sigma_3} - \frac{1}{\varepsilon_D - \Sigma_3}. \quad (52)$$

Here also Σ_3 can be disregarded beside W, μ, ε_D , then the two $-1/\varepsilon_D$ terms cancel out with that from Eq. 48. Now, combining Eqs. 48-52, we obtain

$$G_0 = (\varepsilon - \Sigma_0)\rho_0 \left[\frac{W}{\mu(W - \mu)} - \frac{\pi}{2\Delta} \left(\operatorname{arccosh} \frac{\Delta + \Sigma_1}{\varepsilon - \Sigma_0} + \operatorname{arccosh} \frac{\Delta - \Sigma_1}{\varepsilon - \Sigma_0} - i\pi \right) \right], \quad (53)$$

and

$$G_1 = \Sigma_1 \rho_0 \left[\frac{W}{\mu(W - \mu)} - \frac{2i\pi}{\sqrt{(\varepsilon - \Sigma_0)^2 - (\Delta + \Sigma_1)^2} + \sqrt{(\varepsilon - \Sigma_0)^2 - (\Delta - \Sigma_1)^2}} \right].$$

At least, G_3 is obtained after

$$\begin{aligned} \int_{-\varepsilon_D + \Sigma_3}^{\varepsilon_D + \Sigma_3} \frac{xdx}{z^2 - x^2} &= \frac{1}{2} \ln \frac{(\varepsilon_D - \Sigma_3)^2 - z^2}{(\varepsilon_D + \Sigma_3)^2 - z^2}, \\ \int_{\varepsilon_D + \Sigma_3}^{W - \mu + \Sigma_3} \frac{xdx}{z^2 - x^2} &= \frac{1}{2} \ln \frac{(\varepsilon_D + \Sigma_3)^2 - z^2}{(W - \mu + \Sigma_3)^2 - z^2}, \\ \int_{-\mu + \Sigma_3}^{-\varepsilon_D + \Sigma_3} \frac{xdx}{z^2 - x^2} &= \frac{1}{2} \ln \frac{(\mu - \Sigma_3)^2 - z^2}{(\varepsilon_D - \Sigma_3)^2 - z^2}, \\ \frac{1}{2\Delta} \int_{-\Delta + \Sigma_1}^{\Delta + \Sigma_1} y^2 dy &= \frac{\Delta^2}{3} + \Sigma_1^2, \end{aligned}$$

in the form

$$G_3 = \rho_0 \left\{ \ln \frac{\mu}{W - \mu} + 2\Sigma_3 \frac{(\varepsilon - \sigma_0)^2 - \Delta^2/3 - \Sigma_1^2}{\varepsilon_D^3} \right\}. \quad (54)$$

10 Appendix E

Search for solutions of Eq. 5 in the form of GE consists in consecutive iterations of its r.h.s., separating systematically the GF's already present in previous iterations [27]. Let us start from M-diagonal SPGF $\hat{G}_{\mathbf{k}}$, than the iteration sequence begins with singling out the scattering term with $\hat{G}_{\mathbf{k}}$ itself from those with $\hat{G}_{\mathbf{k}', \mathbf{k}}$, $\mathbf{k}' \neq \mathbf{k}$:

$$\hat{G}_{\mathbf{k}} = \hat{G}_{\mathbf{k}}^{(0)} + \hat{G}_{\mathbf{k}}^{(0)} \frac{1}{N} \sum_{\mathbf{k}', \mathbf{p}} e^{i(\mathbf{k} - \mathbf{k}') \cdot \mathbf{p}} \hat{V} \hat{G}_{\mathbf{k}', \mathbf{k}} =$$

$$= \hat{G}_{\mathbf{k}}^{(0)} + c\hat{G}_{\mathbf{k}}^{(0)}\hat{V}\hat{G}_{\mathbf{k}} + \hat{G}_{\mathbf{k}}^{(0)}\hat{V}\frac{1}{N}\sum_{\mathbf{k}'\neq\mathbf{k},\mathbf{p}}e^{i(\mathbf{k}-\mathbf{k}')\cdot\mathbf{p}}\hat{G}_{\mathbf{k}',\mathbf{k}}. \quad (55)$$

Then for each $\hat{G}_{\mathbf{k}',\mathbf{k}}$ we write down again Eq. 5 and separate the scattering terms with $\hat{G}_{\mathbf{k}}$ and $\hat{G}_{\mathbf{k}',\mathbf{k}}$ in its r.h.s:

$$\begin{aligned} \hat{G}_{\mathbf{k}',\mathbf{k}} &= \hat{G}_{\mathbf{k}'}^{(0)}\hat{V}\frac{1}{N}\sum_{\mathbf{k}'',\mathbf{p}'}e^{i(\mathbf{k}'-\mathbf{k}'')\cdot\mathbf{p}}\hat{G}_{\mathbf{k}'',\mathbf{k}} = \\ &= c\hat{G}_{\mathbf{k}'}^{(0)}\hat{V}\hat{G}_{\mathbf{k}',\mathbf{k}} + \hat{G}_{\mathbf{k}'}^{(0)}\hat{V}\frac{1}{N}e^{i(\mathbf{k}'-\mathbf{k})\cdot\mathbf{p}}\hat{G}_{\mathbf{k}} + \hat{G}_{\mathbf{k}'}^{(0)}\hat{V}\frac{1}{N}\sum_{\mathbf{p}'\neq\mathbf{p}}e^{i(\mathbf{k}'-\mathbf{k})\cdot\mathbf{p}'}\hat{G}_{\mathbf{k}} + \\ &\quad + \hat{G}_{\mathbf{k}'}^{(0)}\hat{V}\frac{1}{N}\sum_{\mathbf{k}''\neq\mathbf{k},\mathbf{k}';\mathbf{p}'}e^{i(\mathbf{k}'-\mathbf{k}'')\cdot\mathbf{p}'}\hat{G}_{\mathbf{k}'',\mathbf{k}}. \end{aligned} \quad (56)$$

Note that the $\mathbf{p}' = \mathbf{p}$ term which gives the phase factor $e^{i(\mathbf{k}'-\mathbf{k})\cdot\mathbf{p}}$ in the r.h.s. of Eq. 56, coherent to that already figured in the last sum in Eq. 55, is explicitly separated from incoherent ones, $e^{i(\mathbf{k}'-\mathbf{k})\cdot\mathbf{p}'}$, $\mathbf{p}' \neq \mathbf{p}$ (but there will be no such separation when doing 1st iteration of Eq. 5 for M-non-diagonal SPGF $\hat{G}_{\mathbf{k}',\mathbf{k}}$ itself). Continuing the sequence, we shall explicitly collect the terms with the initial function $\hat{G}_{\mathbf{k}}$, resulted from: i) all multiple scatterings on the same site $\mathbf{p}$ and ii) on the same pair of sites $\mathbf{p}$ and $\mathbf{p}' \neq \mathbf{p}$. Then summing of i) in $\mathbf{p}$ produces the first term of GE, and, if the pair processes are neglected, it will coincide with the well known CPA result [30]. The second term of GE, obtained by summing of ii) in $\mathbf{p}, \mathbf{p}' \neq \mathbf{p}$, contains interaction matrices $\hat{A}_{\mathbf{p}',\mathbf{p}}$ generated by multiply scattered functions $\hat{G}_{\mathbf{k}',\mathbf{k}}$, $\mathbf{k}' \neq \mathbf{k}$, etc., (including their own renormalization). For instance, the iteration for a function $\hat{G}_{\mathbf{k}'',\mathbf{k}}$ with $\mathbf{k}'' \neq \mathbf{k}, \mathbf{k}'$ in the last term in Eq. 56 will give:

$$\begin{aligned} \hat{G}_{\mathbf{k}'',\mathbf{k}} &= \hat{G}_{\mathbf{k}''}^{(0)}\hat{V}\frac{1}{N}\sum_{\mathbf{k}''',\mathbf{p}''}e^{i(\mathbf{k}''-\mathbf{k}''')\cdot\mathbf{p}''}\hat{G}_{\mathbf{k}''',\mathbf{k}} = \\ &= \hat{G}_{\mathbf{k}''}^{(0)}\hat{V}\frac{1}{N}e^{i(\mathbf{k}''-\mathbf{k})\cdot\mathbf{p}}\hat{G}_{\mathbf{k}} + \hat{G}_{\mathbf{k}''}^{(0)}\hat{V}\frac{1}{N}e^{i(\mathbf{k}''-\mathbf{k})\cdot\mathbf{p}'}\hat{G}_{\mathbf{k}} + \\ &\quad + \text{terms with } \hat{G}_{\mathbf{k}',\mathbf{k}} \text{ and } \hat{G}_{\mathbf{k}'',\mathbf{k}} + \text{terms with } \hat{G}_{\mathbf{k}''',\mathbf{k}} \text{ } (\mathbf{k}''' \neq \mathbf{k}, \mathbf{k}', \mathbf{k}''). \end{aligned} \quad (57)$$

Consequently, the GE for $\hat{G}_{\mathbf{k}}$ obtains the form given by Eq. 6.

Now turn to TPGF $\ll c_{-\mathbf{k}_1,\downarrow}c_{\mathbf{k}_2,\uparrow}|c_{-\mathbf{k}_2+\mathbf{q},\downarrow}c_{\mathbf{k}_1-\mathbf{q},\uparrow} \gg$, beginning from EM's in absence of scattering which develop into a 4×4 matrix form:

$$\begin{aligned} \hat{B}(\xi_1, \xi_2, \Delta_1, \Delta_2) f &= \delta_{0,\mathbf{q}}d, \quad (58) \\ \hat{B}(\xi_1, \xi_2, \Delta_1, \Delta_2) &= \begin{pmatrix} \varepsilon - \xi_1 - \xi_2 & \Delta_1 & \Delta_2 & 0 \\ \Delta_1 & \varepsilon + \xi_1 - \xi_2 & 0 & \Delta_2 \\ \Delta_2 & 0 & \varepsilon - \xi_1 + \xi_2 & \Delta_1 \\ 0 & \Delta_2 & \Delta_1 & \varepsilon + \xi_1 + \xi_2 \end{pmatrix}, \end{aligned}$$

with 4-vectors:

$$f = \begin{pmatrix} \ll c_{-\mathbf{k}_1, \downarrow} c_{\mathbf{k}_2, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \\ \ll c_{\mathbf{k}_1, \uparrow}^+ c_{\mathbf{k}_2, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \\ \ll c_{-\mathbf{k}_1, \downarrow} c_{-\mathbf{k}_2, \downarrow}^+ | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \\ \ll c_{\mathbf{k}_1, \uparrow}^+ c_{-\mathbf{k}_2, \downarrow}^+ | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \end{pmatrix}, \quad d = \begin{pmatrix} 2\Delta_1 \Delta_2 \\ \Delta_1 \\ \Delta_2 \\ 2 \end{pmatrix},$$

and $\xi_1 \equiv \xi_{\mathbf{k}_1}$, $\xi_2 \equiv \xi_{\mathbf{k}_2}$, $\Delta_1 \equiv \Delta_{\mathbf{k}_1}$, $\Delta_2 \equiv \Delta_{\mathbf{k}_2}$. The solution to Eq. 58: $f = \delta_{0, \mathbf{q}} \hat{B}^{-1}(\xi_1, \xi_2, \Delta_1, \Delta_2) d$, gives just the result of Eq. 37 for the 1st component of f .

In presence of scattering, we consider only the M-non-diagonal ($\mathbf{q} \neq 0$) case, then Eq. 58 turns into:

$$\hat{B}(\xi_1, \xi_2, \Delta_1, \Delta_2) f = -\frac{1}{N} \sum_{\mathbf{p}} \left(e^{-i\mathbf{q} \cdot \mathbf{p}} \hat{A}_1 f'_1 + e^{i\mathbf{q} \cdot \mathbf{p}} \hat{A}_2 f'_2 \right), \quad (59)$$

where the vectors of “single scattered” TPGF’s are

$$f'_1 = \begin{pmatrix} \ll c_{-\mathbf{k}_1 + \mathbf{q}, \downarrow} c_{\mathbf{k}_2, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \\ \ll c_{\mathbf{k}_1 - \mathbf{q}, \uparrow}^+ c_{\mathbf{k}_2, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \\ \ll c_{-\mathbf{k}_1 + \mathbf{q}, \downarrow} c_{-\mathbf{k}_2, \downarrow}^+ | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \\ \ll c_{\mathbf{k}_1 - \mathbf{q}, \uparrow}^+ c_{-\mathbf{k}_2, \downarrow}^+ | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \end{pmatrix},$$

$$f'_2 = \begin{pmatrix} \ll c_{-\mathbf{k}_1, \downarrow} c_{\mathbf{k}_2 - \mathbf{q}, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \\ \ll c_{\mathbf{k}_1, \uparrow}^+ c_{\mathbf{k}_2 - \mathbf{q}, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \\ \ll c_{-\mathbf{k}_1, \downarrow} c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow}^+ | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \\ \ll c_{\mathbf{k}_1, \uparrow}^+ c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow}^+ | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg \end{pmatrix},$$

and the 4×4 matrices:

$$\hat{A}_1 = \begin{pmatrix} \hat{V} & 0 \\ 0 & \hat{V} \end{pmatrix}, \quad \hat{A}_2 = \begin{pmatrix} \hat{V} \hat{\tau}_3 & 0 \\ 0 & -\hat{V} \hat{\tau}_3 \end{pmatrix}.$$

Next, EM’s for $f'_{1,2}$:

$$\hat{B}(\xi'_1, \xi_2, \Delta'_1, \Delta_2) f'_1 = -\frac{1}{N} e^{-i\mathbf{q} \cdot \mathbf{p}} \hat{A}_1 f'', \quad (60)$$

$$\hat{B}(\xi_1, \xi'_2, \Delta_1, \Delta'_2) f'_2 = -\frac{1}{N} e^{-i\mathbf{q} \cdot \mathbf{p}} \hat{A}_2 f'',$$

with $\xi'_1 \equiv \xi_{\mathbf{k}_1 - \mathbf{q}}$, $\xi'_2 \equiv \xi_{\mathbf{k}_2 - \mathbf{q}}$, $\Delta'_1 \equiv \Delta_{\mathbf{k}_1 - \mathbf{q}}$, $\Delta'_2 \equiv \Delta_{\mathbf{k}_2 - \mathbf{q}}$, contain the “double scattered” TPGF $f'' \equiv \ll c_{-\mathbf{k}_1 + \mathbf{q}, \downarrow} c_{\mathbf{k}_2 - \mathbf{q}, \uparrow} | c_{-\mathbf{k}_2 + \mathbf{q}, \downarrow} c_{\mathbf{k}_1 - \mathbf{q}, \uparrow} \gg$, which is already M-diagonal and hence can be taken just in the form of Eq. 37. Finally, the solution

$$f = \hat{B}^{-1}(\xi_1, \xi_2, \Delta_1, \Delta_2) \left\{ \delta_{0, \mathbf{q}} + \frac{c}{N} \left[\hat{A}_1 \hat{B}^{-1}(\xi'_1, \xi_2, \Delta'_1, \Delta_2) \hat{A}_1 + \right. \right. \quad (61)$$

$$\left. \left. + \hat{A}_2 \hat{B}^{-1}(\xi_1, \xi'_2, \Delta_1, \Delta'_2) \hat{A}_2 \right] \hat{B}^{-1}(\xi'_1, \xi'_2, \Delta'_1, \Delta'_2) \right\} d,$$

defines the contribution $\sim c(V_L\Delta/V)^2$ into δ^2 , Eq. 36, the factor Δ^2 being due to Δ_1, Δ_2 -odd terms from $\widehat{B}^{-1}(\xi_1, \xi_2, \Delta_1, \Delta_2)$ and $1/V^2$ due to dominating, zeroth order in Δ_1, Δ_2 , terms from $\widehat{B}^{-1}(\xi'_1, \xi_2, \Delta'_1, \Delta_2)$ $\widehat{B}^{-1}(\xi'_1, \xi'_2, \Delta'_1, \Delta'_2)$ and $\widehat{B}^{-1}(\xi_1, \xi'_2, \Delta_1, \Delta'_2)$ $\widehat{B}^{-1}(\xi'_1, \xi'_2, \Delta'_1, \Delta'_2)$.

References

- [1] P.W. Anderson, J. Phys. Chem. Solids **11**, 26 (1959).
- [2] A.A. Abrikosov and L.P. Gor'kov, Sov. Phys. JETP **12**, 1243 (1961).
- [3] Z.-X. Shen and D.S. Dessau, Phys. Rep. **253**, 1 (1995).
- [4] V.M. Loktev, Low Temp. Phys. **22**, 3 (1996).
- [5] A.V. Puchkov, D.N. Basov, and T. Timusk, J. Phys.: Condens. Matter **8**, 10049 (1996).
- [6] V.M. Loktev, R.M. Quick, and S.G. Sharapov, Preprint cond-mat/0012082; Phys. Rep. (to be published, 2001).
- [7] D. Bonn, S. Kamal, K. Zhang, R. Liang, D.J. Baar, E. Klein, and W.N. Hardy, Phys. Rev. **B50**, 4051 (1994).
- [8] A. Maeda, T. Yabe, S. Takebayashi, M. Hase, and K. Uchinokura, Phys. Rev. **B41**, 4112 (1990);
- [9] M.I. Salkola, A.V. Balatsky, R.J. Schrieffer, Phys. Rev. **B55**, 12 648 (1997).
- [10] Y. Fukuzumi, K. Mizuhashi, K. Takenaka, and S. Ushida, Phys. Rev. Lett. **76**, 684 (1996).
- [11] S.H. Pan, E.W. Hudson, K.M. Lang, H. Esaki, S. Ushida, and J.C. Davis, Nature **403**, 746 (2000).
- [12] P.A. Lee, Phys. Rev. Lett. **73**, 1887 (1993).
- [13] A.V. Balatsky, A. Rozengren, and B.L. Altshuler, Phys. Rev. Lett. **73**, 720 (1994).
- [14] Yu.G. Pogorelov, Solid State Commun. **95**, 245 (1995).
- [15] A.M. Nersesyan, A. Tsvelik, F. Wenger, Nucl. Phys. **B438**, 561 (1995).
- [16] A. Ghosal, M. Randeria, and N. Triverdi, Preprint cond-mat/0012304 (2000).
- [17] A.C. Durst and P.A. Lee, Phys. Rev. **B62**, 1270 (2000).
- [18] N.F. Mott and E.A. Davis, Electronic Processes in Non-Crystalline Materials, Clarendon Press, Oxford (1971).

- [19] V.M. Loktev, Yu.G. Pogorelov, *Physica C* **272**, 151 (1996).
- [20] C.C. Tsuei, J.R. Kirtley, C.C. Chi, L.S. Yu-Jahnes, A. Gupta, T. Shaw, J.Z. Sun, and M.B. Ketchen, *Phys. Rev. Lett.* **73**, 593 (1994).
- [21] D.J. Scalapino, *Phys. Rep.* **250**, 329 (1995).
- [22] D.J. Van Harlingen, *Rev. Mod. Phys.* **67**, 515 (1995).
- [23] A.A. Abrikosov, Preprint cond-mat/9912394 (2000); *Phys. Rev.* **B63**, 134518 (2001).
- [24] P.W. Anderson, *Phys. Rev.* **102**, 1492 (1958).
- [25] I.M. Lifshitz, *Adv. Phys.* **13**, 483 (1964).
- [26] I.M. Lifshitz, S.A. Gredeskul, and L.A. Pastur, *Introduction to the Theory of Disordered Systems*, Wiley & Sons, New York (1988).
- [27] M.A. Ivanov, *Sov. Phys. Solid State*, **12**, 1508 (1971).
- [28] M.A. Ivanov, V.M. Loktev, and Yu.G. Pogorelov, *Phys. Rep.* **153**, 209 (1987).
- [29] Yu. Kagan and Ya.A. Iosilevskii, *Sov. Phys. JETP* **15**, 182 (1962).
- [30] R.J. Elliott, J.A. Krumhansl, P.L. Leath, *Rev. Mod. Phys.* **46**, 465 (1974).
- [31] M.A. Ivanov, V.M. Loktev, and Yu.G. Pogorelov, *Sov. Phys. JETP* **74**, 317 (1992).
- [32] L.P. Gor'kov and P.A. Kalugin, *Sov. Phys. JETP Lett.* **41**, 253 (1985).
- [33] M. Covington, M. Aprili, E. Paraoanu, L.H. Greene, F. Xu, J. Zhu, C.A. Mirkin, *Phys. Rev. Lett.* **79**, 277 (1997).




Figure 1: Density of states in a *d*-wave SC system (heavy solid line). Thin solid line shows the non-perturbed $\rho^{(0)}(\varepsilon)$, arrow indicates the solution for $\text{Re}[(1 + V_L G_3)^2 - V_L^2 G_0^2] = 0$ corresponding to the low-energy resonance (other solution at $\varepsilon \approx \Delta$ is not resonant) at the choice of parameters $W = 2$ eV, $V_L = 0.5$ eV, $c = 0.1$.




Figure 2: Schematic of consecutive scattering processes (see Appendix E), bringing an M-non-diagonal TPGF f , through intermediate, partly M-diagonal f_1' and f_2' , to fully M-diagonal f'' : solid vectors standing for l.h.s. operators get fully nested with dashed vectors for r.h.s.